

Perdure U46

water-based aliphatic polyurethane (gloss)



DESCRIPTION

Perdure U46 is a two component water-based aliphatic (non-yellowing) polyurethane topcoat for concrete and wood surfaces. It is free from the health and environmental problems normally found in solvent-based polyurethanes, while maintaining excellent performance properties. It is a high performance coating for use in variety of seamless floor and wall coating systems. Perdure U46 provides a matte finish suitable in areas like clean rooms, hospitals, pharmaceutical facilities, stained concrete and wood floors.

ADVANTAGES

- Low odor during application and cure
- Fast dry and re-coat time
- Low VOC
- Excellent adhesion
- Superior abrasion resistance

SUBSTRATE REQUIREMENTS

- Substrate temperature must be a minimum of 50° F and relative humidity below 85% for proper curing.
- Substrate must be free of dirt, waxes, curing agents and other foreign materials
- Cure times will be extended in conditions of high humidity and poor ventilation

COMPOSITION

Perdure U46 is formulated based on aliphatic polyisocyanate.

COLOR SELECTION

Perdure U46 is available in clear formulations only.

APPLICATION

Surface Preparation is the most critical portion of any successful resinous flooring system application. All substrates must be properly prepared as outlined in Duraamen's technical Bulletin #1. Work must be performed by trained or experienced contractors or maintenance personnel.

INSTALLATION STEPS

- Mix each component (Part A and Part B) separately prior to combining.
- Mix 6 Parts A with 1 Part B. Mix for 1 to 2 minutes. Add 20% water and mix again for at least 2 to 3 minutes with a slow speed drill and paddle.
- Mix **ONLY** the amount of material that can be used in 60 minutes!
- In hot weather conditions work during the cooler times of the day.

CLEAN UP

Clean skin with soap and water. Tools and equipment should be cleaned with Xylene or Lacquer thinner. Consult MSDS for safety and health precautions.

COVERAGE

Perdure U46 covers 7 to 8 m² per liter at 50 microns dry film thickness. Thicker applications may result in bubbling in the cured film. Recoat time is approximately 8–10 hours at 24°C. Application of at least two coats is recommended in high traffic areas like restaurants, retail shops, schools, etc.

MAINTENANCE

After completing the installation, the applicator should provide the owner with maintenance instructions. If floors become slippery due to animal fats, oil, grease, or soap film, clean and rinse thoroughly. Perdure U46 is easily cleaned with neutral soaps or detergents. Routine mechanical scrubbing is recommended for all surfaces having a non-skid texture. Treating the surface with a floor finish (Smartgard) is optional. Long periods of heavy traffic may cause wear patterns necessitating application of a finish coat. **DO NOT** leave any type of tape on the sealer for more than 5 to 10 minutes. Test first in an inconspicuous area for compatibility between the tape and the sealer.

TECHNICAL SERVICE

Duraamen International FZ-LLC. provides services and consultations on material selection, specification, troubleshooting, and other information on the proper repair and protection of concrete surfaces.

SYSTEM PERFORMANCE PROPERTIES

Technical Data		
Pot Life	120min @ 20°C	60min @ 30°C
Dry to Touch	1 hours @ 20°C	1 hour @ 30°C
Walkable	18 hours @ 20°C	12 hours @ 30°C
Solid Content (vol)	39+/-3% (Mixed)	
Mix Ratio	A:B :: 6:1 (by Volume)	
Dilute	With Water 20% (by volume)	
VOC	< 30g/lit	

IMPORTANT! Store in a cool ventilated place. Shelf life is 12 months from the date of manufacture.

CAUTION! SAFETY INFORMATION

USE ONLY WITH ADEQUATE VENTILATION. WEAR PROTECTIVE CLOTHING AND EYE PROTECTION. This product may cause eye, nose and throat irritation. Avoid contact with eyes and skin. Avoid inhaling vapors and spray mist. Open windows and doors to ensure fresh air entry during application and drying. If you experience headaches, dizziness, eye watering or irritation, introduce more fresh air. A properly used respirator (NIOSH approved for organic vapor with P series particulate pre-filter) will offer additional protection. Seek professional advice before using a respirator. A dust mask does not provide protection against vapors. Avoid contact with eyes and skin. Wash thoroughly after handling. Close the container after each use.

FIRST AID: If you experience difficulty breathing, leave the area immediately and seek fresh air. If breathing difficulty continues, seek immediate medical attention. In the case of eye contact, immediately flush eyes with water for at least 20 minutes and get medical attention. If skin comes into contact with the product, wash the contact area thoroughly with soap and water. If swallowed, get immediate medical attention. KEEP OUT OF REACH OF CHILDREN! DO NOT TAKE INTERNALLY!

WARRANTY

Information regarding Duraamen products is based upon extensive research provided by the supplier of the raw materials. By making such information available, Duraamen International FZ-LLC. does not assume any liability beyond express terms of our standard limited material warranty. Duraamen International does not warrant the accuracy or completeness of any such information, whether conveyed orally or in writing, but to the best of our knowledge believe it to be accurate. We reserve the right at any time and without notice to update or improve our products and process for the intended use or application. Duraamen International (Duraamen) warrants for a period of one (1) year that its products will be free of manufacturing defects and will be in conformity with published specifications when handled, stored, mixed and applied in accordance with recommendations of Duraamen. If any product fails to meet this warranty, the liability of Duraamen will be limited to replacement of any non-conforming material if notice of such non-conformity is given to Duraamen within 1 (one) year of delivery of materials. Duraamen may in its discretion refund the price received by Duraamen in lieu of replacing the material. No customer, distributor, or representative of Duraamen is authorized to change or modify the published specifications of this warranty in anyway. In order to obtain replacement or refund the customer must provide written notice containing full details of the non-conformity. Duraamen reserves the right to inspect the non-conforming material prior to replacement EXCEPT FOR THE EXPRESSED WARRANTY STATED ABOVE, THERE ARE NO OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATION, ANY IMPLIED WARRANTY OR MERCHANTABILITY OR FITNESS FOR PURPOSE. DURAAMEN'S OBLIGATION SHALL NOT EXTEND BEYOND THE OBLIGATIONS EXPRESSLY UNDERTAKEN ABOVE AND DURAAMEN SHALL HAVE NO LIABILITY OR RESPONSIBILITY TO THE PURCHASER OR ANY THIRD PARTY FOR ANY LOSS, COST EXPENSE, DAMAGE OR LIABILITY, WHETHER DIRECT OR INDIRECT, OR FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.

Duraamen International FZ-LLC
Shed 15, Warehouse 11-12, Al Hamra Industrial Zone,
PO Box No: 1044, Ras Al Khaimah, UAE
duraamen.ae | info@duraamen.ae | +971 7 2081625

Duraamen Engineered Products, Inc.
20 Haypress Road, Suite 323
Cranbury, NJ 08512, USA
duraamen.com | info@duraamen.com | 1.866.835.6595